

Spessore / Thickness / Stärke / Epaisseur	0,68 mm
Peso tessuto / Weight / Gewicht / Poids (ISO 2286-2)	850 g/m²
Altezza del tessuto / Roll width / Breite / Laize	300 cm



LAQUERED



DOUBLE FACE



FIRE RESISTANT



WATERPROOF



5 YEARS

	IT	EN	DE	FR
Composizione / Material Zusammensetzung Composition	100% Poliestere HT spalmato PVC	100% PVC coated HT Polyester	100% Polyesterträger HT PVC-beschichte	100% Polyester haute ténacité avec enduction PVC
Caratteristiche / Features / Eigenshaften / Caracteristiques	Blockout	Blockout	Blockout	Blockout
Finissaggio / Finishing Ausrüstung / Finitions	Laccato PU	PU coating	Lackiert PU	Lacqué PU
Trattamento / Treatment Behandlung / Traitement	Antimuffa	Mold resistant	Schimmelresistent	Antimoississure
Biocidi / Biocides Biozide / Biocidas (528/2012)	DCOIT	DCOIT	DCOIT	DCOIT
Filato / Yarn / Garn / Fil	PES 1100 Dtex - 1100 Dtex	PES 1100 Dtex - 1100 Dtex	PES 1100 Dtex - 1100 Dtex	PES 1100 Dtex - 1100 Dtex
Costruzione / Construction Einstellung / Contexture	8 fili/cm - 8 fili/cm	8 yarn/cm - 8 yarn/cm	8 Fäden/cm - 8 Fäden/cm	8 fil/cm - 8 fil/cm
Lunghezza rotolo Roll length Rollenlänge Longueur de la pièce	60 m	60 m	60 m	60 m
Resistenza alla trazione Breaking strength Reisskraft Résistance à la traction (ISO 1421-1)	250 daN/5 cm 230 daN/5 cm	250 daN/5 cm 230 daN/5 cm	250 daN/5 cm 230 daN/5 cm	250 daN/5 cm 230 daN/5 cm
Resistenza allo strappo Tear strength Weiterreißfestigkeit Résistance à la déchirure (DIN 53363)	27 daN 27 daN	27 daN 27 daN	27 daN 27 daN	27 daN 27 daN
Adesione / Adhesion / Haftung / Adhérence (ISO 2411)	10 daN/5 cm	10 daN/5 cm	10 daN/5 cm	10 daN/5 cm
Ignifugazione Flammability Entflammbarkeit Ignifugation (UNI 9177)-(NF P92-507) (DIN 4102-1)-(EN 13501-1)	CL.2 (IT) B1 (DE) M2 (FR) B-s2,d0	CL.2 (IT) B1 (DE) M2 (FR) B-s2,d0	CL.2 (IT) B1 (DE) M2 (FR) B-s2,d0	CL.2 (IT) B1 (DE) M2 (FR) B-s2,d0
Solidità dei colori agli UV UV Colour fastness UV Beständigkeit Solidité des couleurs UV (ISO 105 B02)	7/8	7/8	7/8	7/8
Resistenza alle temperature Temperature resistance Temperaturbeständigkeit Résistance à la température (DIN EN 1876-2)	-40°C / +70°C	-40°C / +70°C	-40°C / +70°C	-40°C / +70°C